BMC 300F

BMC 300F is a dishware material, which can produce the toughest foodwares. BMC 300F provides high surface hardness, high gloss, smooth profile, molded-in color, food contact safety, which is suitable for both oven and microwave uses.

HEALTH AND SAFETY INFORMATION

Direct contact with this material may cause minimal eye and skin irritation. Wash thoroughly after handling. For detailed handling instructions refer to the BMC, Inc. Material Safety Data Sheet (MSDS) for this product.

IMPORTANT NOTICE

The information and statements contained herein are believed to be reliable, but are not to be construed as a warranty of any kind. The manufacturer makes no claims regarding the fitness or suitability of this product for use in any specific application. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS OR MERCHANTABILITY FOR A PARTICULAR PURPOSE IS EXPRESSED OR IMPLIED. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license. THE MANUFACTURER'S LIABILITY FOR CLAIMS ARISING OUT OF THE SALE OF THIS PRODUCT IS LIMITED TO REPLACEMENT ONLY AND IT EXPRESSLY DISCLAIMS ANY LIABILITY FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES.

TYPICAL PROPERTIES

Molding

Temperature, °C	130~180
Mold shrinkage, %	0.25~0.40
Specific gravity, g/cm ³	1.70~1.90

Mechanical-Physical (Tested by in-house ISO compression molding bars)

Flexural strength, MPa	100~140
Tensile strength, MPa	25~45
Impact strength, notched Izod, kJ/m ²	20~40
Barcol hardness	30~50

Thermal

Heat distortion temperature, °C	220+
UL Flame resistance 3.0 mm, Color: All	HB
It is not UL listed material	
FDA 21 CFR 177.2420	Pass

Bulk Molding Compounds, Inc. 1600 Powis Court West Chicago, IL 60185 630-377-1065 630-377-7395 Fax Bulk Molding Compounds, Inc. 12600 Eckel Road Perrysburg, OH 43551 19-874-7941 419-874-0951 Fax

BMC (Dongguan) Limited No. 8 Qiaoxin Road Qiaotou Dongguan, Guangdong P.R. China, Postal Code 523525 86-769-8345 2480 Ext. 218 86-769-8334 2028 Fax





^{**}Above test values may be affected by the molding process